

Environmental Product Declaration



Concrete BC Member Industry-Wide EPD for
READY-MIXED CONCRETE



ASTM International Certified Environmental Product Declaration

Declared Product	This Environmental Product Declaration (EPD) covers concrete mixes produced by Concrete BC members.	
Declaration Owner	Concrete BC 26162-30A Avenue, Langley, BC V4W 2W5, Canada Phone: 604-626-4141 Website: www.concretebc.ca	
Program Operator	ASTM International 100 Bar Harbor Drive West Conshohocken, PA 19428-2959, USA Website: www.astm.org	 ASTM INTERNATIONAL Helping our world work better
LCA and EPD Developer	Athena Sustainable Materials Institute 280 Albert Street, Suite 404 Ottawa, ON K1P 5G8, Canada Website: www.athenasmi.org	 Athena Sustainable Materials Institute
Core PCR	ISO 21930:2017 Sustainability in Building Construction - Environmental Declaration of Building Products	
Sub-category PCR	NSF International Product Category Rule (PCR) for Concrete Version 2.1 (August 2021), Verified by Thomas P. Gloria, Ph.D., Industrial Ecology Consultants	
Independent LCA Reviewer and EPD Verifier	Independent verification of the declaration and data, according to ISO 21930:2017 and ISO 14025:2006 <input type="checkbox"/> Internal <input checked="" type="checkbox"/> External	Thomas P. Gloria, Ph.D., Industrial Ecology Consultants, ASTM International
Date of Issue	July 27, 2022	
Period of Validity	5 Years – Valid until July 27, 2027	
EPD Number	EPD 348	
The declared product meets the following product specifications:	<p>Disclaimer: EPDs are comparable only if they comply with this document, use the same sub-category PCR where applicable, include all relevant information modules and are based on equivalent scenarios with respect to the context of construction works.</p> <p>The ready mixed concrete products represented in this EPD are comprised of (in order of greatest mass per mix): natural and crushed aggregates, Portland cement, fly ash/slag cement, batch water, and admixtures.</p>	
<ul style="list-style-type: none"> • ACI 211: Standard Practice for Selecting Proportions for Normal, Heavyweight, and Mass Concrete • CSA A3000: Cementitious materials compendium • CSA A23.1/A23.2 Concrete materials and methods of concrete construction/Test methods and standard practices for concrete • ACI 318: Building Code Requirements for Structural Concrete • ASTM C94 Standard Specification for Ready-Mixed Concrete • CSI MasterFormat Division 03-30-00: Cast-in-Place Concrete • UNSPSC Code 30111500: Ready Mix 		

Methodology of Underlying LCA

Declared Unit

The declared unit is 1 cubic metre of ready mixed concrete. Products covered by this EPD satisfy general purpose concrete as used in residential, commercial and public works applications in Canada. Key product variables include:

- **28-day strength** – Different compressive strengths were considered (28 days unless otherwise noted);
- **Slag cement/Fly Ash** – Varies between 0% and 50%;
- **Admixture use** – The use of air-entraining, water reducing, and high range water reducing admixture varies;
- **Aggregate use** – The use of crushed coarse, crushed fine, natural coarse, and natural fine aggregates varies.

Product (mix design) components include the following: Portland cement (GU), Portland limestone cement (GUL), slag cement, fly ash, natural and crushed aggregates, admixtures and batch water.

Scope

The modeled concrete mixes included benchmarks for each strength class. This EPD is intended for use in Business to Business (B-to-B) communication. This EPD can only be used and referenced by members of Concrete BC as having participated in the study. The scope of this EPD is cradle-to-gate and considers the following life cycle stages.

- **A1 - Raw Material Supply:** Includes all upstream processes related to extraction, handling, and processing of the raw materials and intermediate component products as well as fuels used in the production of concrete. Component products include cement, supplementary cementitious materials, aggregate (coarse and fine), water, admixtures and other materials or chemicals used in concrete mixtures.
- **A2 - Transportation:** Accounts for the transportation of all input materials and fuels from the supplier to the gate of the concrete plant.
- **A3 - Manufacturing (Core Processes):** Includes all core processes and the energy and water used to store, move, batch and mix the concrete and operate the concrete plant as well as the transportation and processing of wastes from these core processes.

Building Life Cycle Information Modules															
Product stage			Construction Process stage		Use stage						End-of-life stage				
Raw Material supply	Transport	Manufacturing	Transport	Construction/Installation	Use	Maintenance	Repair	Replacement	Refurbishment	Operational Energy Use	Operational Water Use	De-Construction/ Demolition	Transport	Waste processing	Disposal
A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4

Figure 1: Life cycle stage schematic – alpha-numeric designations as per NSF PCR 2021

Description of Product

This EPD presents results for the range of products that are available across British Columbia. For each specified mix, variations were developed based on the use of GU and GUL cement as well as different SCM replacement levels. For each mix, a “baseline” mix was developed that represents the average product mix within British Columbia. The mixes presented in this EPD utilize the following naming convention:

Mix Name: Identify the 28-day specified compressive strength of the proposed product by type of cement unless otherwise noted. Portland cement, also known as Type I or General Use cement is labeled as “GU”. Portland limestone cement, also known as Type IL or General Use Limestone cement is labeled as “GUL”. The name of the mix also notes whether it is “air entrained” and also includes other specifications of the mix recognized in the marketplace. For instance, mixes may also be tagged with an exposure class – (C) classes pertain to chloride exposure; (F) classes pertain to freezing and thawing exposure without chlorides; (N) class is exposed to neither chlorides nor freezing and thawing. For more information concerning exposure class see CSA standard A23.1

SCM Replacement: Identify the supplementary cementing material (SCM) percentage. Fly ash is labeled in the mix designs as “FA”, slag cement as “SC”, and silica fume blended cement is labeled as “GUbSF”. For example, a mix with 20% fly ash is denoted in the mix identifier as “20 FA”.

Cut-off Rules

The cut-off criteria for all activity stage flows considered within the system boundary conform with ISO 14044:2006 and NSF PCR 2021. Specifically, the cut-off criteria were applied as follows:

- All inputs and outputs for which data are available are included in the calculated effects and no collected core process data are excluded.
- A one percent cut-off is considered for renewable and non-renewable primary energy consumption and the total mass of inputs within a unit process. The sum of the total neglected flows does not exceed 5% of all energy consumption and mass of inputs.
- All flows known to contribute a significant impact or to uncertainty are included.
- The cut-off rules are not applied to hazardous and toxic materials – all are included in the life cycle inventory.

Allocation

The allocation of co-products or secondary flows cross the system boundary conforms with ISO 21930: 2017 Section 7.2.4. Specifically, the allocation criteria were applied as follows:

- Allocation was not applied any of the gate-to-gate production facilities. For facilities that manufacture additional products (i.e. aggregate), the LCI flows at the facility specific to the concrete production were reported.
- For secondary data sources, the NSF PCR default allocation selection (i.e. “Cut-off” or “Alloc Rec”) was applied.
- The product category rules for this EPD recognize fly ash, silica fume and slag as recovered materials and thus the environmental impacts allocated to these materials are limited to the treatment and transportation required to use as a concrete material input
- A portion (30%) of the reported fleet energy use for truck mixing plants was allocated to the mixing facility.

Participation

Participation in the concrete plant data collection was open to all members of the Ready Mixed Concrete Association of British Columbia (Concrete BC). Concrete plants were randomly selected based on size of operation and geographic distribution. The results of this report are applicable to the concrete produced from all members of Concrete BC and a list of certified concrete plants can be found on the Association website (concretebc.ca).

Data Sources and Software

This EPD is based on foreground LCI data collected from the participating companies' production facilities. A representative sample of Concrete BC member facilities were selected based on technical attributes, production scale, and geographic location. In total, 24 facilities operated by Concrete BC member companies completed LCI data collection questionnaires representing over 21% of all Concrete BC member facilities.

All upstream material, resource and energy carrier inputs have been sourced from various industry-average datasets and literature as specified for use in NSF PCR 2021. Tables 2 to 4 describe each LCI data source for raw materials (A1), transportation by mode (A2), the core manufacture process (A3), and descriptions of data quality for each data source.

This EPD was calculated using manufacturer specific cement data that represents 100% of the total cement used in this mix. As part of the data collection process, each participating facility provided data as to their cement supplier. All cement facilities were represented with environmental product declarations, and thus a weighted average cement profile was created for each individual region.

Table 2. A1 - Raw Material Supply

Materials	LCI Data Source	Geography	Year	Data Quality Assessment
General Use Cement ASTM C150, C595, C1157, CSA A300	Weighted Average of Results Specific to Concrete Producers in Region	Canada	2020-2021	<ul style="list-style-type: none"> • Technology: very good • Time: very good • Geography: very good • Completeness: very good • Reliability: very good
General Use Limestone Cement ASTM C150, C595, C1157, CSA A3000	Weighted Average of Results Specific to Concrete Producers in Region	Canada	2020-2021	<ul style="list-style-type: none"> • Technology: very good • Time: very good • Geography: very good • Completeness: very good • Reliability: very good
Fly Ash ASTM C618, CSA A3000	None, no incoming burden, only inbound transport was considered	N/A	N/A	<ul style="list-style-type: none"> • N/A • Recovered material
Slag Cement ASTM C989, CSA A3000	Slag Cement Association N. America EPD Slag Cement, 2021	N. America	2021	<ul style="list-style-type: none"> • Technology: good • Process models ground granulated blast furnace slag • Time: good • Data is within 3 years • Geography: good • Completeness: good • Reliability: very good, third-party verified EPD
Crushed Aggregates coarse and fine ASTM C33, CSA A23.1/A23.2	ecoinvent 3.4: Gravel, crushed {RoW} production Cut-off, U Modified with regional electricity	EU/Canada	2004	<ul style="list-style-type: none"> • Technology: good • Time: fair • Data is twelve years old but technology remains consistent across the industry
Natural Aggregates coarse and fine ASTM C30, CSA A23.1/A23.2	ecoinvent 3.4: Gravel, round {RoW} gravel and sand quarry operation Cut-off, U Modified with regional electricity	EU/Canada	2004	<ul style="list-style-type: none"> • Geography: good • Swiss production (modified with regional Electricity). • Completeness: very good • Reliability: very good
Admixtures ASTM C494, ASTM C260	EFCIA EPDs for Air Entrainers, Plasticisers and superplasticisers (2015)	EU	2015	<ul style="list-style-type: none"> • Technology: very good • Time: good • Geography: good • Completeness: good • Reliability: good
Water ASTM C1602, CSA A23.1/A23.2	Non-supported LCIA indicators estimated	Global	2011	<ul style="list-style-type: none"> • Technology: good • Process models ground granulated blast furnace slag • Time: good • Data is within 3 years • Geography: good • Completeness: good • Reliability: very good, third-party verified EPD

Table 3. A2 - Transportation

Process	LCI Data Source	Geography	Year	Data Quality Assessment
Truck Transportation	USLCI 2014: Transport, combination truck, short-haul, diesel powered/tkm/RNA	USA	2007	<ul style="list-style-type: none"> • Technology: good • Time: fair • Geography: very good • Completeness: good • Reliability: good
Rail Transportation	USLCI 2014: Transport, train, diesel powered /US U	USA	2007	<ul style="list-style-type: none"> • Technology: good • Time: fair • Geography: very good • Completeness: good • Reliability: good
Ocean Transportation	USLCI 2014: Transport, ocean freighter, average fuel mix /US U	USA	2007	<ul style="list-style-type: none"> • Technology: good • Time: fair • Geography: very good • Completeness: good • Reliability: good

Table 4. A3 - Manufacturing

Process	LCI Data Source	Geography	Year	Data Quality Assessment
Electricity	ecoinvent 3.4: Electricity, low voltage, at grid, (CA)	Regional	2015	<ul style="list-style-type: none"> • Technology: very good • Time: good • Geography: very good • Completeness: good • Reliability: good
Natural Gas	USLCI 2014: Natural gas, combusted in industrial boiler/US	US	2008	<ul style="list-style-type: none"> • Technology: very good • Time: fair • Geography: fair • Completeness: good • Reliability: good
Diesel	USLCI 2014: Diesel, combusted in industrial equipment/US	US	2008	<ul style="list-style-type: none"> • Technology: very good • Time: fair • Geography: fair • Completeness: good • Reliability: good
Liquefied Propane Gas	USLCI 2014: Liquefied petroleum gas, combusted in industrial boiler/US	US	2008	<ul style="list-style-type: none"> • Technology: very good • Time: fair • Geography: fair • Completeness: good • Reliability: good
Hazardous Waste	ecoinvent 3.4: Hazardous waste, for incineration {ROW} treatment of hazardous waste, hazardous waste incineration Alloc Rec, U	EU	2008	<ul style="list-style-type: none"> • Technology: good • Time: fair • Geography: fair • Completeness: very good • Reliability: very good
Non-Hazardous Waste	ecoinvent 3.4: Inert waste {RoW} treatment of, sanitary landfill Alloc Rec, U	EU	2008	<ul style="list-style-type: none"> • Technology: good • Time: fair • Geography: fair • Completeness: very good • Reliability: very good

Athena's Concrete LCA Software V2 was used to gather the facility data, mix designs, and to conduct the LCA modeling. This software was third party reviewed and found to be in conformance with the following relevant standards: ISO 14040:2006b, ISO 14044:2006c, ISO 14025:2006, ISO 21930:2017, and the NSF PCR 2021.

Life Cycle Assessment Results

The LCA results presented in this EPD are intended for use in Business to Business (B-to-B) communication. The EPD supports 25 life cycle impact assessment indicators and inventory metrics as listed in Table 5. The Impact Assessment method and other calculation methodologies are specified in Table 4. Tables 5 through 27 present the LCA results for the mixes produced at the different facilities (Information module A1-A3 accumulated). The results are presented first based on a declared unit of 1 cubic metre.

Table 4. Life Cycle Category Indicators and Inventory Metrics

Core Mandatory Impact Indicator	Abbreviation	Unit	Method/Source
Global warming potential	GWP	kg CO ₂ e	TRACI 2.1 V1.02
Depletion potential of the stratospheric ozone layer	ODP	kg CFC11e	TRACI 2.1 V1.02
Acidification potential of soil and water sources	AP	kg SO ₂ e	TRACI 2.1 V1.02
Eutrophication potential	EP	kg Ne	TRACI 2.1 V1.02
Photochemical smog creation potential	POCP	kg O ₃ e	TRACI 2.1 V1.02
Abiotic depletion potential (ADPfossil)*	ADPf	MJ, NCV	CML-IA Baseline V3.02
Abiotic depletion potential (ADPelements)*	ADPe	kg Sbe	CML-IA Baseline V3.02
Use of Primary Resources			
Renewable primary energy carrier used as energy*	RPRE	MJ, NCV	CED V1.10 NCV
Renewable primary energy carrier used as material*	RPRM	MJ, NCV	LCI Indicator
Non-renewable primary energy carrier used as energy*	NRPRE	MJ, NCV	CED V1.10 NCV
Non-renewable primary energy carrier used as material*	NRPRM	MJ, NCV	LCI Indicator
Secondary Material, Secondary Fuel and Recovered Energy			
Secondary material*	SM	kg	LCI Indicator
Renewable secondary fuel *	RSF	MJ, NCV	LCI Indicator
Non-renewable secondary fuel*	NRSF	MJ, NCV	LCI Indicator
Recovered energy*	RE	MJ, NCV	LCI Indicator
Mandatory Inventory Parameters			
Consumption of freshwater resources;	FW	m ³	LCI Indicator
Calcination and carbonation emissions	CCE	kg CO ₂ e	LCI Indicator
Indicators Describing Waste			
Hazardous waste disposed*	HWD	kg	LCI Indicator
Non-hazardous waste disposed*	NHWD	kg	LCI Indicator
High-level radioactive waste*	HLRW	m ³	LCI Indicator
Intermediate- and low-level radioactive waste*	ILLRW	m ³	LCI Indicator
Components for re-use*	CRU	kg	LCI Indicator
Materials for recycling*	MR	kg	LCI Indicator
Materials for energy recovery*	MER	kg	LCI Indicator
Recovered energy exported from the product system*	EE	MJ, NCV	LCI Indicator

Emerging LCA impact categories and inventory items are still under development and can have high levels of uncertainty that preclude international acceptance pending further development. Use caution when interpreting data in categories marked with (*) in Table 5. Additionally, EPDs are comparable only if they comply with this document, use the same sub-category PCR where applicable, include all relevant information modules and are based on equivalent scenarios with respect to the context of construction works. No regulated substances of very high concern were identified in the LCA.

Table 5. LCA Results 15 MPa Concrete without air (N)

Unit	Baseline 15 MPa Concrete without air (N) GU 30 SCM	15 MPa Concrete without air (N) GU	15 MPa Concrete without air (N) GU 15 SCM	15 MPa Concrete without air (N) GU 25 SCM	15 MPa Concrete without air (N) GU 40 SCM	15 MPa Concrete without air (N) GUL	15 MPa Concrete without air (N) GUL 15 SCM	15 MPa Concrete without air (N) GUL 25 SCM	15 MPa Concrete without air (N) GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	179.42	229.82	204.62	188.44	163.07	213.35	190.63	176.06	153.16
ODP	kg CFC-11 eq.	7.56E-06	8.04E-06	7.80E-06	7.67E-06	7.40E-06	7.63E-06	7.44E-06	7.35E-06	7.14E-06
EP	kg N eq.	0.17	0.19	0.18	0.17	0.16	0.18	0.17	0.16	0.15
AP	kg SO ₂ eq.	0.86	0.88	0.87	0.87	0.86	0.84	0.84	0.83	0.83
POCP	kg O ₃ eq.	19.15	19.82	19.48	19.31	18.93	18.80	18.62	18.55	18.32
Use of primary resources										
RPR _E	MJ, NCV	105.43	128.97	117.20	109.62	97.80	127.79	116.20	108.74	97.09
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1265.90	1406.85	1336.38	1293.24	1220.19	1090.30	1067.44	1055.18	1029.74
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	71.49	102.24	86.86	76.89	61.51	92.50	78.59	69.56	55.65
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	543.95	594.90	569.42	553.48	527.43	578.54	555.52	541.17	517.58
ADPe	kg Sb	1.02E-04	1.08E-04	1.05E-04	1.03E-04	9.98E-05	1.07E-04	1.04E-04	1.02E-04	9.93E-05
Consumption of freshwater resources										
FW	m ³	2.12	2.28	2.20	2.15	2.06	2.23	2.16	2.11	2.03
Waste and output flows										
HWD	kg	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
NHWD	kg	39.62	56.64	48.13	42.61	34.10	51.15	43.46	38.48	30.79
HLRW	m ³	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09
ILLRW	m ³	5.77E-08	5.77E-08	5.77E-08	5.77E-08	5.77E-08	5.77E-08	5.77E-08	5.77E-08	5.77E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	82.44	117.91	100.18	88.67	70.94	106.90	90.82	80.39	64.31

Table 6. LCA Results 20 MPa Concrete with air (N)

Unit	Baseline 20 MPa Concrete with air (N) GU 20 SCM	20 MPa Concrete with air (N) GU	20 MPa Concrete with air (N) GU 15 SCM	20 MPa Concrete with air (N) GU 25 SCM	20 MPa Concrete with air (N) GU 40 SCM	20 MPa Concrete with air (N) GUL	20 MPa Concrete with air (N) GUL 15 SCM	20 MPa Concrete with air (N) GUL 25 SCM	20 MPa Concrete with air (N) GUL 40 SCM	
		20 MPa Concrete with air (N) GU	20 MPa Concrete with air (N) GU 15 SCM	20 MPa Concrete with air (N) GU 25 SCM	20 MPa Concrete with air (N) GU 40 SCM	20 MPa Concrete with air (N) GUL	20 MPa Concrete with air (N) GUL 15 SCM	20 MPa Concrete with air (N) GUL 25 SCM	20 MPa Concrete with air (N) GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	193.86	226.55	202.03	185.69	161.17	210.42	188.31	173.57	151.46
ODP	kg CFC-11 eq.	7.60E-06	7.92E-06	7.68E-06	7.53E-06	7.29E-06	7.51E-06	7.34E-06	7.22E-06	7.04E-06
EP	kg N eq.	0.17	0.19	0.18	0.17	0.16	0.18	0.17	0.16	0.15
AP	kg SO ₂ eq.	0.87	0.89	0.87	0.87	0.86	0.84	0.84	0.83	0.83
POCP	kg O ₃ eq.	19.46	19.90	19.57	19.35	19.02	18.90	18.72	18.60	18.43
Use of primary resources										
RPR _E	MJ, NCV	113.36	128.62	117.18	109.54	98.10	127.47	116.20	108.68	97.40
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1306.75	1398.18	1329.61	1283.90	1215.33	1088.06	1065.82	1050.99	1028.74
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	80.21	100.16	85.20	75.23	60.27	90.62	77.08	68.06	54.52
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	568.30	601.35	576.56	560.04	535.25	585.32	562.93	548.00	525.61
ADPe	kg Sb	1.05E-04	1.09E-04	1.06E-04	1.04E-04	1.01E-04	1.08E-04	1.05E-04	1.03E-04	1.00E-04
Consumption of freshwater resources										
FW	m ³	2.23	2.34	2.26	2.20	2.12	2.29	2.21	2.16	2.09
Waste and output flows										
HWD	kg	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
NHWD	kg	44.45	55.49	47.21	41.69	33.41	50.11	42.63	37.64	30.17
HLRW	m3	1.90E-09	1.90E-09	1.90E-09	1.90E-09	1.90E-09	1.90E-09	1.90E-09	1.90E-09	1.90E-09
ILLRW	m3	6.26E-08	6.26E-08	6.26E-08	6.26E-08	6.26E-08	6.26E-08	6.26E-08	6.26E-08	6.26E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	92.51	115.51	98.26	86.76	69.50	104.73	89.08	78.65	63.01

Table 7. LCA Results 20 MPa Concrete without air (N)

Unit	Baseline 20 MPa Concrete without air (N) GU 20 SCM	20 MPa Concrete without air (N) GU	20 MPa Concrete without air (N) GU 15 SCM	20 MPa Concrete without air (N) GU 25 SCM	20 MPa Concrete without air (N) GU 40 SCM	20 MPa Concrete without air (N) GUL	20 MPa Concrete without air (N) GUL 15 SCM	20 MPa Concrete without air (N) GUL 25 SCM	20 MPa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	194.73	227.42	202.90	186.55	162.03	211.29	189.18	174.44	152.33
ODP kg CFC-11 eq.	7.62E-06	7.94E-06	7.70E-06	7.54E-06	7.30E-06	7.53E-06	7.35E-06	7.23E-06	7.05E-06
EP kg N eq.	0.17	0.19	0.18	0.17	0.16	0.18	0.17	0.16	0.15
AP kg SO ₂ eq.	0.88	0.89	0.88	0.88	0.86	0.85	0.85	0.84	0.84
POCP kg O ₃ eq.	19.66	20.10	19.77	19.55	19.22	19.10	18.92	18.80	18.62
Use of primary resources									
RPR _E MJ, NCV	114.72	129.98	118.53	110.90	99.45	128.83	117.55	110.03	98.76
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	1321.67	1413.10	1344.52	1298.81	1230.24	1102.98	1080.73	1065.90	1043.65
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	80.21	100.16	85.20	75.23	60.27	90.62	77.08	68.06	54.52
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	582.28	615.33	590.54	574.02	549.23	599.30	576.90	561.98	539.59
ADPe kg Sb	1.15E-04	1.19E-04	1.16E-04	1.14E-04	1.11E-04	1.18E-04	1.15E-04	1.13E-04	1.10E-04
Consumption of freshwater resources									
FW m ³	2.27	2.38	2.30	2.25	2.16	2.33	2.26	2.21	2.13
Waste and output flows									
HWD kg	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
NHWD kg	44.45	55.49	47.21	41.69	33.41	50.11	42.63	37.64	30.17
HLRW m ³	1.92E-09	1.92E-09	1.92E-09	1.92E-09	1.92E-09	1.92E-09	1.92E-09	1.92E-09	1.92E-09
ILLRW m ³	6.48E-08	6.48E-08	6.48E-08	6.48E-08	6.48E-08	6.48E-08	6.48E-08	6.48E-08	6.48E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	92.51	115.51	98.26	86.76	69.50	104.73	89.08	78.65	63.01

Table 8. LCA Results 25 MPa Concrete with air (F-2)

Unit	Baseline 25 MPa Concrete with air (F-2) GU 20 SCM	with air (F-2)								
		25 MPa Concrete GU	25 MPa Concrete GU 15 SCM	25 MPa Concrete GU 25 SCM	25 MPa Concrete GU 40 SCM	25 MPa Concrete GUL	25 MPa Concrete GUL 15 SCM	25 MPa Concrete GUL 25 SCM	25 MPa Concrete GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	230.52	270.02	240.06	220.30	190.33	250.48	223.46	205.65	178.62
ODP	kg CFC-11 eq.	9.09E-06	9.47E-06	9.18E-06	8.99E-06	8.69E-06	8.97E-06	8.76E-06	8.61E-06	8.40E-06
EP	kg N eq.	0.20	0.22	0.21	0.20	0.19	0.21	0.19	0.19	0.18
AP	kg SO ₂ eq.	1.00	1.01	1.00	0.99	0.98	0.96	0.96	0.95	0.95
POCP	kg O ₃ eq.	22.05	22.58	22.18	21.91	21.51	21.37	21.15	21.01	20.79
Use of primary resources										
RPR _E	MJ, NCV	129.91	148.36	134.37	125.14	111.15	146.96	133.18	124.10	110.31
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1521.90	1632.38	1548.57	1493.33	1409.52	1256.63	1229.44	1211.52	1184.33
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	97.26	121.36	103.07	91.02	72.73	109.79	93.25	82.35	65.80
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	631.45	671.39	641.09	621.13	590.83	651.96	624.60	606.56	579.19
ADPe	kg Sb	1.27E-04	1.32E-04	1.28E-04	1.26E-04	1.22E-04	1.31E-04	1.28E-04	1.25E-04	1.22E-04
Consumption of freshwater resources										
FW	m ³	2.29	2.42	2.32	2.25	2.15	2.36	2.27	2.21	2.11
Waste and output flows										
HWD	kg	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
NHWD	kg	53.88	67.23	57.10	50.43	40.31	60.70	51.56	45.54	36.40
HLRW	m ³	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09
ILLRW	m ³	5.91E-08	5.91E-08	5.91E-08	5.91E-08	5.91E-08	5.91E-08	5.91E-08	5.91E-08	5.91E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	112.16	139.96	118.87	104.97	83.88	126.89	107.77	95.17	76.05

Table 9. LCA Results 25 MPa Concrete without air (N)

Unit	Baseline 25 MPa Concrete without air (N) GU 20 SCM	25 MPa Concrete without air (N) GU	25 MPa Concrete without air (N) GU 15 SCM	25 MPa Concrete without air (N) GU 25 SCM	25 MPa Concrete without air (N) GU 40 SCM	25 MPa Concrete without air (N) GUL	25 MPa Concrete without air (N) GUL 15 SCM	25 MPa Concrete without air (N) GUL 25 SCM	25 MPa Concrete without air (N) GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	219.70	257.85	229.24	211.02	182.24	239.24	213.44	197.03	171.07
ODP	kg CFC-11 eq.	8.67E-06	9.04E-06	8.76E-06	8.61E-06	8.30E-06	8.56E-06	8.36E-06	8.25E-06	8.02E-06
EP	kg N eq.	0.19	0.21	0.20	0.19	0.18	0.20	0.19	0.18	0.17
AP	kg SO ₂ eq.	0.96	0.98	0.96	0.96	0.94	0.93	0.92	0.92	0.91
POCP	kg O ₃ eq.	21.27	21.78	21.40	21.20	20.77	20.63	20.42	20.34	20.08
Use of primary resources										
RPR _E	MJ, NCV	124.56	142.37	129.01	120.48	107.07	141.04	127.88	119.48	106.27
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1457.37	1564.03	1484.03	1435.18	1352.60	1206.30	1180.35	1166.24	1137.71
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	92.27	115.54	98.09	86.86	69.41	104.53	88.74	78.59	62.79
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	609.84	648.39	619.48	601.47	571.97	629.90	603.78	587.56	560.86
ADPe	kg Sb	1.20E-04	1.25E-04	1.21E-04	1.19E-04	1.15E-04	1.24E-04	1.21E-04	1.18E-04	1.15E-04
Consumption of freshwater resources										
FW	m ³	2.26	2.39	2.29	2.23	2.13	2.33	2.24	2.19	2.10
Waste and output flows										
HWD	kg	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
NHWD	kg	51.12	64.00	54.34	48.13	38.47	57.80	49.07	43.46	34.74
HLRW	m ³	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09
ILLRW	m ³	5.90E-08	5.90E-08	5.90E-08	5.90E-08	5.90E-08	5.90E-08	5.90E-08	5.90E-08	5.90E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	106.41	133.25	113.12	100.18	80.05	120.80	102.55	90.82	72.57

Table 10. LCA Results 30 MPa Concrete with air (F-2)

Unit	Baseline 30 MPa Concrete with air (F-2) GU 20 SCM	30 MPa Concrete with air (F-2)								
		GU	GU 15 SCM	GU 25 SCM	GU 40 SCM	GUL	GUL 15 SCM	GUL 25 SCM	GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	269.83	317.51	282.09	258.25	222.83	294.22	262.28	240.78	208.85
ODP	kg CFC-11 eq.	1.07E-05	1.12E-05	1.08E-05	1.06E-05	1.03E-05	1.06E-05	1.03E-05	1.02E-05	9.90E-06
EP	kg N eq.	0.24	0.26	0.24	0.23	0.22	0.24	0.23	0.22	0.20
AP	kg SO ₂ eq.	1.14	1.16	1.14	1.13	1.12	1.09	1.09	1.08	1.08
POCP	kg O ₃ eq.	24.95	25.59	25.12	24.80	24.33	24.15	23.89	23.72	23.46
Use of primary resources										
RPR _E	MJ, NCV	147.17	169.43	152.89	141.76	125.23	167.77	151.48	140.52	124.23
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1748.38	1881.71	1782.66	1716.00	1616.95	1433.90	1401.77	1380.14	1348.01
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	115.54	144.64	123.02	108.48	86.86	130.85	111.30	98.14	78.59
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADP _f	MJ, LHV	692.72	740.91	705.11	681.01	645.21	717.76	685.42	663.65	631.31
ADP _e	kg Sb	1.42E-04	1.48E-04	1.43E-04	1.40E-04	1.36E-04	1.47E-04	1.42E-04	1.39E-04	1.35E-04
Consumption of freshwater resources										
FW	m ³	2.36	2.52	2.40	2.32	2.20	2.44	2.34	2.26	2.15
Waste and output flows										
HWD	kg	0.02	0.03	0.02	0.02	0.02	0.03	0.02	0.02	0.02
NHWD	kg	64.01	80.11	68.15	60.10	48.13	72.34	61.54	54.27	43.47
HLRW	m ³	1.80E-09	1.80E-09							
ILLRW	m ³	5.65E-08	5.65E-08							
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	133.25	166.80	141.88	125.10	100.18	151.22	128.63	113.42	90.82

Table 11. LCA Results 30 MPa Concrete without air (N)

Unit	Baseline 30 MPa Concrete without air (N) GU 20 SCM	30 MPa Concrete without air (N) GU	30 Mpa Concrete without air (N) GU 15 SCM	30 Mpa Concrete without air (N) GU 25 SCM	30 Mpa Concrete without air (N) GU 40 SCM	30 MPa Concrete without air (N) GUL	30 Mpa Concrete without air (N) GUL 15 SCM	30 Mpa Concrete without air (N) GUL 25 SCM	30 Mpa Concrete without air (N) GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	258.92	303.87	269.82	247.34	213.28	281.65	250.94	230.67	199.96
ODP	kg CFC-11 eq.	1.03E-05	1.07E-05	1.04E-05	1.01E-05	9.81E-06	1.01E-05	9.88E-06	9.72E-06	9.47E-06
EP	kg N eq.	0.23	0.25	0.23	0.22	0.21	0.23	0.22	0.21	0.20
AP	kg SO ₂ eq.	1.10	1.12	1.10	1.09	1.08	1.06	1.05	1.05	1.04
POCP	kg O ₃ eq.	24.19	24.79	24.33	24.03	23.58	23.42	23.17	23.01	22.76
Use of primary resources										
RPR _E	MJ, NCV	141.95	162.94	147.04	136.55	120.65	161.35	145.69	135.36	119.70
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1681.49	1807.20	1711.96	1649.11	1553.87	1379.98	1349.08	1328.69	1297.79
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	110.56	137.99	117.21	103.49	82.71	124.83	106.03	93.63	74.83
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	672.55	717.99	683.57	660.84	626.42	695.91	664.81	644.28	613.18
ADPe	kg Sb	1.34E-04	1.39E-04	1.35E-04	1.32E-04	1.28E-04	1.38E-04	1.34E-04	1.31E-04	1.27E-04
Consumption of freshwater resources										
FW	m ³	2.35	2.50	2.39	2.31	2.20	2.43	2.33	2.26	2.16
Waste and output flows										
HWD	kg	0.02	0.03	0.02	0.02	0.02	0.02	0.02	0.02	0.02
NHWD	kg	61.25	76.43	64.93	57.34	45.83	69.02	58.63	51.77	41.39
HLRW	m3	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09
ILLRW	m3	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	127.50	159.13	135.17	119.35	95.38	144.27	122.54	108.20	86.47

Table 12. LCA Results 32 MPa Concrete with air (C-2)

Unit	Baseline 32 MPa Concrete with air (C-2) GU 20 SCM	32 MPa Concrete with air (C-2)	32 MPa Concrete GU	32 MPa Concrete GU 15 SCM	32 MPa Concrete GU 25 SCM	32 MPa Concrete GU 40 SCM	32 MPa Concrete GUL	32 MPa Concrete GUL 15 SCM	32 MPa Concrete GUL 25 SCM	32 MPa Concrete GUL 40 SCM
Environmental impacts										
GWP	kg CO ₂ eq.	285.31	335.71	298.25	273.05	234.90	311.01	277.23	254.51	220.11
ODP	kg CFC-11 eq.	1.13E-05	1.18E-05	1.15E-05	1.12E-05	1.08E-05	1.12E-05	1.09E-05	1.07E-05	1.05E-05
EP	kg N eq.	0.25	0.27	0.26	0.24	0.23	0.25	0.24	0.23	0.21
AP	kg SO ₂ eq.	1.19	1.21	1.20	1.19	1.17	1.15	1.14	1.14	1.13
POCP	kg O ₃ eq.	26.11	26.78	26.28	25.94	25.43	25.25	24.98	24.80	24.52
Use of primary resources										
RPR _E	MJ, NCV	154.63	178.16	160.67	148.90	131.09	176.39	159.17	147.58	130.04
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	1841.76	1982.72	1877.95	1807.48	1700.81	1507.89	1473.90	1451.03	1416.43
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	122.61	153.36	130.51	115.13	91.85	138.75	118.07	104.15	83.10
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADP _f	MJ, LHV	723.07	774.02	736.15	710.68	672.12	749.47	715.26	692.25	657.42
ADP _e	kg Sb	1.54E-04	1.60E-04	1.55E-04	1.52E-04	1.47E-04	1.59E-04	1.54E-04	1.51E-04	1.46E-04
Consumption of freshwater resources										
FW	m ³	2.39	2.56	2.44	2.35	2.22	2.48	2.37	2.29	2.18
Waste and output flows										
HWD	kg	0.02	0.03	0.03	0.02	0.02	0.03	0.02	0.02	0.02
NHWD	kg	67.92	84.94	72.29	63.78	50.90	76.70	65.28	57.59	45.96
HLRW	m3	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09
ILLRW	m3	5.62E-08	5.62E-08	5.62E-08	5.62E-08	5.62E-08	5.62E-08	5.62E-08	5.62E-08	5.62E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	141.40	176.87	150.50	132.77	105.93	160.35	136.45	120.37	96.03

Table 13. LCA Results 32 MPa Concrete without air (N)

Unit	Baseline 32 MPa Concrete without air (N) GU 20 SCM	32 Mpa Concrete without air (N) GU	32 Mpa Concrete without air (N) GU 15 SCM	32 Mpa Concrete without air (N) GU 25 SCM	32 Mpa Concrete without air (N) GU 40 SCM	32 Mpa Concrete without air (N) GUL	32 Mpa Concrete without air (N) GUL 15 SCM	32 Mpa Concrete without air (N) GUL 25 SCM	32 Mpa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	272.44	320.80	284.70	261.03	224.08	297.10	264.55	243.23	209.89
ODP kg CFC-11 eq.	1.09E-05	1.13E-05	1.10E-05	1.08E-05	1.04E-05	1.07E-05	1.05E-05	1.03E-05	1.00E-05
EP kg N eq.	0.24	0.26	0.24	0.23	0.22	0.24	0.23	0.22	0.21
AP kg SO ₂ eq.	1.14	1.16	1.15	1.14	1.12	1.10	1.09	1.09	1.08
POCP kg O ₃ eq.	25.09	25.74	25.26	24.99	24.45	24.28	24.01	23.89	23.57
Use of primary resources									
RPR _E MJ, NCV	144.98	167.55	150.70	139.62	122.40	165.86	149.26	138.35	121.38
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	1736.18	1871.41	1770.46	1706.37	1600.94	1415.89	1383.13	1364.08	1328.14
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	117.62	147.13	125.10	110.56	88.11	133.11	113.18	100.02	79.71
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	664.82	713.70	677.21	653.69	615.94	690.15	657.19	636.00	601.83
ADPe kg Sb	1.09E-04	1.15E-04	1.11E-04	1.08E-04	1.03E-04	1.14E-04	1.10E-04	1.07E-04	1.02E-04
Consumption of freshwater resources									
FW m ³	2.33	2.49	2.37	2.29	2.16	2.41	2.30	2.23	2.12
Waste and output flows									
HWD kg	0.02	0.03	0.02	0.02	0.02	0.03	0.02	0.02	0.02
NHWD kg	65.16	81.49	69.30	61.25	48.82	73.59	62.58	55.31	44.09
HLRW m3	1.75E-09	1.75E-09	1.75E-09	1.75E-09	1.75E-09	1.75E-09	1.75E-09	1.75E-09	1.75E-09
ILLRW m3	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	135.65	169.68	144.27	127.50	101.61	153.83	130.80	115.59	92.12

Table 14. LCA Results 35 MPa Concrete with air (F-2)

Unit	Baseline 35 MPa Concrete with air (F-2) GU 20 SCM	35 Mpa Concrete with air (F-2)								
		GU	GU 15 SCM	GU 25 SCM	GU 40 SCM	GUL	GUL 15 SCM	GUL 25 SCM	GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	310.51	365.00	324.13	297.06	255.34	338.09	301.24	276.84	239.21
ODP	kg CFC-11 eq.	1.23E-05	1.28E-05	1.24E-05	1.22E-05	1.18E-05	1.21E-05	1.19E-05	1.17E-05	1.14E-05
EP	kg N eq.	0.27	0.30	0.28	0.27	0.25	0.28	0.26	0.25	0.23
AP	kg SO ₂ eq.	1.28	1.31	1.29	1.28	1.26	1.23	1.22	1.22	1.21
POCP	kg O ₃ eq.	27.94	28.67	28.12	27.81	27.21	27.01	26.71	26.56	26.21
Use of primary resources										
RPR _E	MJ, NCV	168.15	193.59	174.51	161.85	142.39	191.67	172.88	160.40	141.24
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	2004.30	2156.68	2042.39	1968.78	1850.01	1639.38	1602.31	1580.16	1539.89
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	133.83	167.08	142.14	125.52	100.16	151.15	128.59	113.55	90.62
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADP _f	MJ, LHV	785.25	840.33	799.02	772.05	729.48	813.58	776.27	751.97	713.45
ADP _e	kg Sb	1.90E-04	1.96E-04	1.91E-04	1.88E-04	1.83E-04	1.95E-04	1.90E-04	1.87E-04	1.82E-04
Consumption of freshwater resources										
FW	m ³	2.46	2.65	2.51	2.42	2.28	2.56	2.44	2.35	2.23
Waste and output flows										
HWD	kg	0.03	0.03	0.03	0.02	0.02	0.03	0.03	0.02	0.02
NHWD	kg	74.13	92.54	78.73	69.53	55.50	83.56	71.10	62.79	50.12
HLRW	m3	1.79E-09	1.79E-09							
ILLRW	m3	5.59E-08	5.59E-08							
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	154.34	192.68	163.93	144.75	115.51	174.69	148.62	131.23	104.73

Table 15. LCA Results 35 MPa Concrete without air (N)

Unit	Baseline 35 MPa Concrete without air (N) GU 20 SCM	35 Mpa Concrete without air (N) GU SCM	35 Mpa Concrete without air (N) GU 15 SCM	35 Mpa Concrete without air (N) GU 25 SCM	35 Mpa Concrete without air (N) GU 40 SCM	35 Mpa Concrete without air (N) GUL	35 Mpa Concrete without air (N) GUL 15 SCM	35 Mpa Concrete without air (N) GUL 25 SCM	35 Mpa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	293.75	345.52	306.69	280.81	241.99	320.02	285.01	261.67	226.66
ODP kg CFC-11 eq.	1.17E-05	1.22E-05	1.18E-05	1.16E-05	1.12E-05	1.15E-05	1.13E-05	1.11E-05	1.08E-05
EP kg N eq.	0.26	0.28	0.26	0.25	0.23	0.26	0.25	0.24	0.22
AP kg SO ₂ eq.	1.22	1.24	1.23	1.22	1.20	1.17	1.17	1.16	1.16
POCP kg O ₃ eq.	26.75	27.44	26.92	26.57	26.06	25.86	25.58	25.39	25.11
Use of primary resources									
RPR _E MJ, NCV	157.37	181.54	163.42	151.33	133.21	179.72	161.87	149.96	132.11
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	1882.54	2027.30	1918.73	1846.35	1737.78	1537.03	1501.80	1478.32	1443.10
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	126.76	158.35	134.66	118.87	95.18	143.26	121.83	107.54	86.11
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADP _f MJ, LHV	728.32	780.65	741.40	715.24	675.99	755.30	719.85	696.21	660.76
ADP _e kg Sb	1.48E-04	1.55E-04	1.50E-04	1.47E-04	1.42E-04	1.54E-04	1.49E-04	1.46E-04	1.41E-04
Consumption of freshwater resources									
FW m ³	2.42	2.59	2.46	2.37	2.24	2.51	2.39	2.31	2.19
Waste and output flows									
HWD kg	0.02	0.03	0.03	0.02	0.02	0.03	0.02	0.02	0.02
NHWD kg	70.22	87.71	74.59	65.85	52.74	79.20	67.36	59.46	47.62
HLRW m3	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09
ILLRW m3	5.57E-08	5.57E-08	5.57E-08	5.57E-08	5.57E-08	5.57E-08	5.57E-08	5.57E-08	5.57E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	146.19	182.62	155.30	137.08	109.76	165.56	140.79	124.28	99.51

Table 16. LCA Results 40 MPa Concrete with air (C-1)

Unit	Baseline 40 Mpa Concrete with air (C-1) GU 20 SCM	40 Mpa Concrete with air (C-1) GU	40 Mpa Concrete with air (C-1) GU 15 SCM	40 Mpa Concrete with air (C-1) GU 25 SCM	40 Mpa Concrete with air (C-1) GU 40 SCM	40 Mpa Concrete with air (C-1) GUL	40 Mpa Concrete with air (C-1) GUL 15 SCM	40 Mpa Concrete with air (C-1) GUL 25 SCM	40 Mpa Concrete with air (C-1) GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	344.04	405.34	359.03	328.38	282.74	375.16	333.39	305.75	264.60
ODP	kg CFC-11 eq.	1.37E-05	1.43E-05	1.39E-05	1.36E-05	1.31E-05	1.35E-05	1.32E-05	1.30E-05	1.27E-05
EP	kg N eq.	0.30	0.33	0.31	0.29	0.27	0.30	0.29	0.27	0.26
AP	kg SO ₂ eq.	1.40	1.42	1.40	1.39	1.37	1.34	1.33	1.33	1.32
POCP	kg O ₃ eq.	30.31	31.13	30.51	30.11	29.50	29.27	28.93	28.71	28.38
Use of primary resources										
RPR _E	MJ, NCV	180.81	209.43	187.80	173.49	152.19	207.27	185.97	171.87	150.89
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	2180.32	2351.74	2222.22	2136.51	2008.89	1771.40	1729.37	1701.57	1660.16
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	150.04	187.45	159.18	140.48	112.63	169.58	144.01	127.09	101.90
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	817.57	879.53	832.71	801.73	755.60	849.53	807.24	779.25	737.58
ADPe	kg Sb	1.81E-04	1.89E-04	1.83E-04	1.79E-04	1.73E-04	1.87E-04	1.82E-04	1.78E-04	1.73E-04
Consumption of freshwater resources										
FW	m ³	2.49	2.70	2.54	2.44	2.28	2.60	2.46	2.36	2.23
Waste and output flows										
HWD	kg	0.03	0.03	0.03	0.03	0.02	0.03	0.03	0.03	0.02
NHWD	kg	83.11	103.81	88.17	77.82	62.40	93.74	79.61	70.27	56.35
HLRW	m3	1.73E-09	1.73E-09	1.73E-09	1.73E-09	1.73E-09	1.73E-09	1.73E-09	1.73E-09	1.73E-09
ILLRW	m3	5.16E-08	5.16E-08	5.16E-08	5.16E-08	5.16E-08	5.16E-08	5.16E-08	5.16E-08	5.16E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	173.03	216.17	183.58	162.01	129.89	195.98	166.43	146.88	117.76

Table 17. LCA Results 40 MPa Concrete without air (N)

Unit	Baseline 40 Mpa Concrete without air (N) GU 20 SCM	40 Mpa Concrete without air (N) GU	40 Mpa Concrete without air (N) GU 15 SCM	40 Mpa Concrete without air (N) GU 25 SCM	40 Mpa Concrete without air (N) GU 40 SCM	40 Mpa Concrete without air (N) GUL	40 Mpa Concrete without air (N) GUL 15 SCM	40 Mpa Concrete without air (N) GUL 25 SCM	40 Mpa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	329.00	387.58	343.99	314.70	271.11	358.93	319.62	293.21	253.91
ODP kg CFC-11 eq.	1.31E-05	1.37E-05	1.32E-05	1.30E-05	1.25E-05	1.29E-05	1.26E-05	1.24E-05	1.21E-05
EP kg N eq.	0.29	0.31	0.29	0.28	0.26	0.29	0.28	0.26	0.25
AP kg SO ₂ eq.	1.36	1.39	1.37	1.35	1.34	1.31	1.30	1.30	1.29
POCP kg O ₃ eq.	29.73	30.52	29.93	29.54	28.96	28.75	28.43	28.22	27.90
Use of primary resources									
RPRE MJ, NCV	175.75	203.10	182.75	169.08	148.72	201.05	181.01	167.54	147.49
RPRM MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPRE MJ, NCV	2109.46	2273.27	2151.36	2069.46	1947.56	1722.52	1682.97	1656.40	1616.85
NRPRM MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	142.14	177.89	151.29	133.41	106.81	160.93	136.87	120.70	96.63
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	814.12	873.33	829.26	799.66	755.59	844.86	805.05	778.30	738.50
ADPe kg Sb	1.82E-04	1.90E-04	1.84E-04	1.81E-04	1.75E-04	1.88E-04	1.83E-04	1.80E-04	1.74E-04
Consumption of freshwater resources									
FW m ³	2.58	2.78	2.64	2.54	2.39	2.69	2.56	2.47	2.33
Waste and output flows									
HWD kg	0.03	0.03	0.03	0.03	0.02	0.03	0.03	0.02	0.02
NHWD kg	78.74	98.52	83.80	73.90	59.18	88.96	75.67	66.73	53.44
HLRW m3	1.87E-09	1.87E-09	1.87E-09	1.87E-09	1.87E-09	1.87E-09	1.87E-09	1.87E-09	1.87E-09
ILLRW m3	6.04E-08	6.04E-08	6.04E-08	6.04E-08	6.04E-08	6.04E-08	6.04E-08	6.04E-08	6.04E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	163.93	205.15	174.47	153.86	123.18	185.99	158.18	139.49	111.68

Table 18. LCA Results 45 MPa Concrete with air (C-1)

Unit	Baseline 45 MPa Concrete with air (C-1) GU 25 SCM	with air (C-1)								
		45 MPa Concrete GU	45 MPa Concrete GU 15 SCM	45 MPa Concrete GU 25 SCM	45 Mpa Concrete GU 40 SCM	45 Mpa Concrete GUL	45 Mpa Concrete GUL 15 SCM	45 Mpa Concrete GUL 25 SCM	45 Mpa Concrete GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	355.65	438.75	389.03	355.65	305.93	406.09	361.25	331.16	286.32
ODP	kg CFC-11 eq.	1.47E-05	1.55E-05	1.50E-05	1.47E-05	1.42E-05	1.46E-05	1.43E-05	1.40E-05	1.37E-05
EP	kg N eq.	0.32	0.35	0.33	0.32	0.29	0.33	0.31	0.30	0.28
AP	kg SO ₂ eq.	1.50	1.54	1.51	1.50	1.48	1.45	1.44	1.43	1.42
POCP	kg O ₃ eq.	32.48	33.59	32.93	32.48	31.82	31.57	31.21	30.97	30.61
Use of primary resources										
RPR _E	MJ, NCV	187.98	226.78	203.56	187.98	164.76	224.44	201.58	186.23	163.36
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	2319.91	2552.29	2413.24	2319.91	2180.86	1924.33	1879.22	1848.94	1803.83
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	152.12	202.82	172.48	152.12	121.78	183.49	156.04	137.62	110.17
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPf	MJ, LHV	874.96	958.95	908.69	874.96	824.70	926.49	881.09	850.61	805.21
ADPe	kg Sb	2.04E-04	2.15E-04	2.09E-04	2.04E-04	1.98E-04	2.13E-04	2.07E-04	2.03E-04	1.97E-04
Consumption of freshwater resources										
FW	m ³	2.57	2.85	2.68	2.57	2.40	2.75	2.59	2.49	2.34
Waste and output flows										
HWD	kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.02
NHWD	kg	84.26	112.33	95.53	84.26	67.47	101.43	86.26	76.09	60.92
HLRW	m3	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09
ILLRW	m3	5.56E-08	5.56E-08	5.56E-08	5.56E-08	5.56E-08	5.56E-08	5.56E-08	5.56E-08	5.56E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	175.43	233.91	198.92	175.43	140.44	212.06	180.34	159.04	127.32

Table 19. LCA Results 45 MPa Concrete without air (N)

Unit	Baseline 45 Mpa Concrete without air (N) GU 25 SCM	45 Mpa Concrete without air (N) GU SCM	45 Mpa Concrete without air (N) GU 15 SCM	45 Mpa Concrete without air (N) GU 25 SCM	45 Mpa Concrete without air (N) GU 40 SCM	45 Mpa Concrete without air (N) GUL SCM	45 Mpa Concrete without air (N) GUL 15 SCM	45 Mpa Concrete without air (N) GUL 25 SCM	45 Mpa Concrete without air (N) GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	335.06	412.71	365.71	335.06	288.07	382.12	339.74	312.11	269.73
ODP	kg CFC-11 eq.	1.38E-05	1.45E-05	1.41E-05	1.38E-05	1.33E-05	1.38E-05	1.34E-05	1.32E-05	1.29E-05
EP	kg N eq.	0.30	0.33	0.31	0.30	0.28	0.31	0.29	0.28	0.26
AP	kg SO ₂ eq.	1.43	1.46	1.44	1.43	1.41	1.38	1.37	1.37	1.36
POCP	kg O ₃ eq.	31.09	32.13	31.50	31.09	30.46	30.24	29.90	29.67	29.33
Use of primary resources										
RPR _E	MJ, NCV	179.00	215.26	193.31	179.00	157.06	213.07	191.46	177.36	155.75
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	2196.36	2413.51	2282.08	2196.36	2064.94	1825.44	1782.80	1754.99	1712.35
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	142.56	189.94	161.26	142.56	113.88	171.84	145.89	128.97	103.03
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPF	MJ, LHV	841.26	919.75	872.25	841.26	793.76	889.35	846.44	818.45	775.53
ADPe	kg Sb	1.99E-04	2.09E-04	2.03E-04	1.99E-04	1.93E-04	2.08E-04	2.02E-04	1.98E-04	1.93E-04
Consumption of freshwater resources										
FW	m ³	2.58	2.84	2.69	2.58	2.42	2.75	2.60	2.51	2.37
Waste and output flows										
HWD	kg	0.03	0.03	0.03	0.03	0.02	0.03	0.03	0.03	0.02
NHWD	kg	78.97	105.19	89.32	78.97	63.09	94.99	80.65	71.31	56.97
HLRW	m3	1.86E-09	1.86E-09	1.86E-09	1.86E-09	1.86E-09	1.86E-09	1.86E-09	1.86E-09	1.86E-09
ILLRW	m3	5.96E-08	5.96E-08	5.96E-08	5.96E-08	5.96E-08	5.96E-08	5.96E-08	5.96E-08	5.96E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	164.40	219.05	185.97	164.40	131.33	198.59	168.60	149.05	119.07

Table 20. LCA Results 50 MPa Concrete with air (C-1) @ 56 days

Unit	Baseline 50 MPa Concrete with air (C-1) GU 25 SCM	50 MPa Concrete with air (C-1)								
		GU	GU 15 SCM	GU 25 SCM	GU 40 SCM	GUL	GUL 15 SCM	GUL 25 SCM	GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	379.60	468.82	415.70	379.60	326.47	433.82	385.91	353.36	305.46
ODP	kg CFC-11 eq.	1.57E-05	1.66E-05	1.60E-05	1.57E-05	1.52E-05	1.57E-05	1.53E-05	1.50E-05	1.46E-05
EP	kg N eq.	0.34	0.38	0.35	0.34	0.31	0.35	0.33	0.32	0.30
AP	kg SO ₂ eq.	1.59	1.63	1.61	1.59	1.57	1.53	1.52	1.52	1.51
POCP	kg O ₃ eq.	34.37	35.56	34.85	34.37	33.66	33.39	33.01	32.75	32.36
Use of primary resources										
RPR _E	MJ, NCV	199.11	240.77	215.96	199.11	174.31	238.27	213.83	197.23	172.80
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	2465.29	2714.81	2566.24	2465.29	2316.72	2041.81	1993.61	1960.86	1912.66
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	162.92	217.37	184.95	162.92	130.51	196.65	167.32	147.39	118.07
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPF	MJ, LHV	918.47	1008.66	954.96	918.47	864.77	973.87	925.36	892.40	843.88
ADPe	kg Sb	2.20E-04	2.31E-04	2.25E-04	2.20E-04	2.14E-04	2.30E-04	2.23E-04	2.19E-04	2.13E-04
Consumption of freshwater resources										
FW	m ³	2.64	2.94	2.76	2.64	2.46	2.83	2.66	2.55	2.39
Waste and output flows										
HWD	kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
NHWD	kg	90.24	120.38	102.44	90.24	72.30	108.70	92.50	81.49	65.29
HLRW	m ³	1.81E-09	1.81E-09							
ILLRW	m ³	5.51E-08	5.51E-08							
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	187.89	250.68	213.29	187.89	150.50	227.27	193.37	170.34	136.45

Table 21. LCA Results 50 MPa Concrete without air (N)

Unit	Baseline 50 MPa Concrete without air (N) GU 25 SCM	50 MPa Concrete without air (N) GU	50 MPa Concrete without air (N) GU 15 SCM	50 MPa Concrete without air (N) GU 25 SCM	50 MPa Concrete without air (N) GU 40 SCM	50 MPa Concrete without air (N) GUL	50 MPa Concrete without air (N) GUL 15 SCM	50 MPa Concrete without air (N) GUL 25 SCM	50 MPa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	359.49	443.95	393.55	359.49	309.09	410.82	365.37	334.66	289.21
ODP kg CFC-11 eq.	1.49E-05	1.57E-05	1.52E-05	1.49E-05	1.44E-05	1.49E-05	1.45E-05	1.43E-05	1.39E-05
EP kg N eq.	0.32	0.36	0.34	0.32	0.30	0.33	0.31	0.30	0.28
AP kg SO ₂ eq.	1.52	1.56	1.53	1.52	1.50	1.46	1.46	1.45	1.44
POCP kg O ₃ eq.	32.96	34.08	33.41	32.96	32.28	32.04	31.67	31.42	31.06
Use of primary resources									
RPR _E MJ, NCV	187.88	227.32	203.78	187.88	164.35	224.95	201.77	186.11	162.93
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	2326.23	2562.42	2421.47	2326.23	2185.28	1925.46	1879.73	1848.83	1803.10
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	154.20	205.73	174.98	154.20	123.44	186.12	158.30	139.50	111.67
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	862.55	947.92	896.97	862.55	811.60	915.00	868.97	837.87	791.85
ADPe kg Sb	1.89E-04	1.99E-04	1.93E-04	1.89E-04	1.82E-04	1.98E-04	1.92E-04	1.88E-04	1.81E-04
Consumption of freshwater resources									
FW m ³	2.62	2.90	2.73	2.62	2.45	2.79	2.64	2.54	2.38
Waste and output flows									
HWD kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.02
NHWD kg	85.41	113.94	96.91	85.41	68.39	102.88	87.51	77.12	61.75
HLRW m3	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09	1.82E-09
ILLRW m3	5.70E-08	5.70E-08	5.70E-08	5.70E-08	5.70E-08	5.70E-08	5.70E-08	5.70E-08	5.70E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	177.83	237.26	201.79	177.83	142.36	215.10	182.94	161.22	129.06

Table 22. LCA Results 50 MPa Concrete withair (C-XL)

Unit	Baseline 50 MPa Concrete withair (C-XL) GU 30 SCM	50 MPa Concrete withair (C-XL) GU	50 MPa Concrete withair (C-XL) GU 15 SCM	50 MPa Concrete withair (C-XL) GU 25 SCM	50 MPa Concrete withair (C-XL) GU 40 SCM	50 MPa Concrete withair (C-XL) GUL	50 MPa Concrete withair (C-XL) GUL 15 SCM	50 MPa Concrete withair (C-XL) GUL 25 SCM	50 MPa Concrete withair (C-XL) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	345.16	446.64	395.56	362.18	311.10	413.38	367.32	337.22	291.16
ODP kg CFC-11 eq.	1.48E-05	1.58E-05	1.53E-05	1.49E-05	1.44E-05	1.49E-05	1.45E-05	1.43E-05	1.39E-05
EP kg N eq.	0.31	0.36	0.34	0.32	0.30	0.33	0.31	0.30	0.28
AP kg SO ₂ eq.	1.52	1.56	1.54	1.52	1.50	1.47	1.46	1.45	1.45
POCP kg O ₃ eq.	32.70	34.06	33.38	32.93	32.25	32.00	31.63	31.39	31.02
Use of primary resources									
RPR _E MJ, NCV	183.69	231.07	207.22	191.64	167.79	228.69	205.20	189.85	166.36
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	2314.53	2598.34	2455.48	2362.15	2219.29	1958.80	1912.45	1882.17	1835.82
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	144.64	206.56	175.39	155.03	123.86	186.88	158.68	140.25	112.05
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	873.14	975.72	924.09	890.35	838.71	942.66	896.02	865.54	818.89
ADPe kg Sb	2.15E-04	2.27E-04	2.21E-04	2.17E-04	2.10E-04	2.26E-04	2.20E-04	2.15E-04	2.09E-04
Consumption of freshwater resources									
FW m ³	2.53	2.87	2.70	2.59	2.42	2.77	2.61	2.51	2.35
Waste and output flows									
HWD kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.02
NHWD kg	80.12	114.40	97.14	85.87	68.62	103.30	87.72	77.54	61.96
HLRW m ³	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09	1.81E-09
ILLRW m ³	5.51E-08	5.51E-08	5.51E-08	5.51E-08	5.51E-08	5.51E-08	5.51E-08	5.51E-08	5.51E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	166.80	238.22	202.27	178.78	142.84	215.97	183.38	162.09	129.50

Table 23. LCA Results 55 MPa Concrete withair (C-XL)

Unit	Baseline 55 MPa Concrete withair (C-XL) GU 25 SCM	55 MPa Concrete withair (C-XL) GU	55 MPa Concrete withair (C-XL) GU 15 SCM	55 MPa Concrete withair (C-XL) GU 25 SCM	55 MPa Concrete withair (C-XL) GU 40 SCM	55 MPa Concrete withair (C-XL) GUL	55 MPa Concrete withair (C-XL) GUL 15 SCM	55 MPa Concrete withair (C-XL) GUL 25 SCM	55 MPa Concrete withair (C-XL) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	402.11	495.93	439.40	402.11	344.72	458.85	407.87	374.27	322.50
ODP kg CFC-11 eq.	1.66E-05	1.75E-05	1.69E-05	1.66E-05	1.60E-05	1.66E-05	1.61E-05	1.59E-05	1.55E-05
EP kg N eq.	0.36	0.40	0.37	0.36	0.33	0.37	0.35	0.33	0.31
AP kg SO ₂ eq.	1.67	1.71	1.69	1.67	1.64	1.61	1.60	1.59	1.58
POCP kg O ₃ eq.	35.98	37.18	36.43	35.98	35.17	34.89	34.48	34.26	33.80
Use of primary resources									
RPR _E MJ, NCV	210.96	254.79	228.39	210.96	184.19	252.14	226.14	208.97	182.60
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	2611.96	2872.24	2714.14	2611.96	2449.38	2159.35	2108.06	2076.65	2022.16
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	172.90	230.25	195.76	172.90	137.99	208.31	177.10	156.42	124.83
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	970.93	1065.36	1008.21	970.93	912.51	1028.51	976.88	943.25	890.43
ADPe kg Sb	2.55E-04	2.67E-04	2.60E-04	2.55E-04	2.48E-04	2.65E-04	2.58E-04	2.54E-04	2.47E-04
Consumption of freshwater resources									
FW m ³	2.68	3.00	2.80	2.68	2.49	2.88	2.70	2.59	2.41
Waste and output flows									
HWD kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
NHWD kg	95.77	127.51	108.42	95.77	76.44	115.14	97.90	86.47	69.03
HLRW m ³	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09	1.78E-09
ILLRW m ³	5.30E-08	5.30E-08	5.30E-08	5.30E-08	5.30E-08	5.30E-08	5.30E-08	5.30E-08	5.30E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	199.39	265.54	225.76	199.39	159.13	240.74	204.67	180.77	144.27

Table 24. LCA Results 55 MPa Concrete without air (N)

Unit	Baseline 55 MPa Concrete without air (N) GU 25 SCM	55 MPa Concrete without air (N) GU	55 MPa Concrete without air (N) GU 15 SCM	55 MPa Concrete without air (N) GU 25 SCM	55 MPa Concrete without air (N) GU 40 SCM	55 MPa Concrete without air (N) GUL	55 MPa Concrete without air (N) GUL 15 SCM	55 MPa Concrete without air (N) GUL 25 SCM	55 MPa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	376.56	465.11	411.98	376.56	323.43	430.37	382.46	350.53	302.62
ODP kg CFC-11 eq.	1.56E-05	1.64E-05	1.59E-05	1.56E-05	1.51E-05	1.56E-05	1.52E-05	1.49E-05	1.45E-05
EP kg N eq.	0.33	0.38	0.35	0.33	0.31	0.35	0.33	0.31	0.29
AP kg SO ₂ eq.	1.59	1.62	1.60	1.59	1.56	1.53	1.52	1.51	1.51
POCP kg O ₃ eq.	34.36	35.54	34.83	34.36	33.65	33.39	33.01	32.75	32.36
Use of primary resources									
RPRE MJ, NCV	196.39	237.73	212.93	196.39	171.59	235.25	210.82	194.53	170.10
RPRM MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPRE MJ, NCV	2436.00	2683.62	2535.05	2436.00	2287.43	2015.77	1967.57	1935.44	1887.23
NRPRM MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	161.68	215.71	183.29	161.68	129.26	195.15	165.82	146.27	116.94
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPf MJ, LHV	901.65	991.15	937.45	901.65	847.94	956.63	908.11	875.77	827.26
ADPe kg Sb	2.05E-04	2.16E-04	2.10E-04	2.05E-04	1.98E-04	2.15E-04	2.08E-04	2.04E-04	1.97E-04
Consumption of freshwater resources									
FW m ³	2.68	2.98	2.80	2.68	2.51	2.87	2.71	2.60	2.44
Waste and output flows									
HWD kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
NHWD kg	89.55	119.46	101.52	89.55	71.61	107.87	91.67	80.86	64.66
HLRW m3	1.84E-09	1.84E-09	1.84E-09	1.84E-09	1.84E-09	1.84E-09	1.84E-09	1.84E-09	1.84E-09
ILLRW m3	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08	5.79E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	186.45	248.76	211.38	186.45	149.07	225.53	191.64	169.04	135.14

Table 25. LCA Results 60 MPa Concrete with air (C-XL)

Unit	Baseline 60 MPa Concrete with air (C-1) GU 25 SCM	with air (C-1)								
		60 MPa Concrete GU	60 MPa Concrete GU 15 SCM	60 MPa Concrete GU 25 SCM	60 MPa Concrete GU 40 SCM	60 MPa Concrete GUL	60 MPa Concrete GUL 15 SCM	60 MPa Concrete GUL 25 SCM	60 MPa Concrete GUL 40 SCM	
Environmental impacts										
GWP	kg CO ₂ eq.	421.88	521.32	462.07	421.88	362.62	482.30	428.87	392.63	339.20
ODP	kg CFC-11 eq.	1.74E-05	1.84E-05	1.78E-05	1.74E-05	1.69E-05	1.74E-05	1.70E-05	1.67E-05	1.63E-05
EP	kg N eq.	0.37	0.42	0.39	0.37	0.35	0.39	0.37	0.35	0.33
AP	kg SO ₂ eq.	1.75	1.79	1.77	1.75	1.72	1.69	1.68	1.67	1.66
POCP	kg O ₃ eq.	37.61	38.93	38.14	37.61	36.82	36.52	36.09	35.80	35.37
Use of primary resources										
RPR _E	MJ, NCV	221.06	267.49	239.82	221.06	193.39	264.70	237.45	218.97	191.72
RPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E	MJ, NCV	2735.82	3013.91	2848.20	2735.82	2570.10	2263.71	2209.94	2173.48	2119.72
NRPR _M	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources										
SM	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF	MJ, NCV	181.63	242.31	206.15	181.63	145.47	219.21	186.50	164.32	131.60
RE	MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential										
ADPF	MJ, LHV	1012.58	1113.10	1053.20	1012.58	952.68	1074.32	1020.21	983.51	929.40
ADPe	kg Sb	2.77E-04	2.90E-04	2.83E-04	2.77E-04	2.70E-04	2.88E-04	2.81E-04	2.76E-04	2.69E-04
Consumption of freshwater resources										
FW	m ³	2.76	3.09	2.89	2.76	2.56	2.97	2.79	2.66	2.48
Waste and output flows										
HWD	kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
NHWD	kg	100.60	134.19	114.17	100.60	80.58	121.17	103.09	90.84	72.77
HLRW	m ³	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09	1.80E-09
ILLRW	m ³	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08	5.42E-08
CRU	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE	kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency										
CCE	kg CO ₂ eq.	209.46	279.44	237.74	209.46	167.76	253.34	215.54	189.90	152.09

Table 26. LCA Results 60 MPa Concrete without air (N)

Unit	Baseline 60 MPa Concrete without air (N) GU 25 SCM	60 MPa Concrete without air (N) GU	60 MPa Concrete without air (N) GU 15 SCM	60 MPa Concrete without air (N) GU 25 SCM	60 MPa Concrete without air (N) GU 40 SCM	60 MPa Concrete without air (N) GUL	60 MPa Concrete without air (N) GUL 15 SCM	60 MPa Concrete without air (N) GUL 25 SCM	60 MPa Concrete without air (N) GUL 40 SCM
Environmental impacts									
GWP kg CO ₂ eq.	400.43	494.43	437.89	400.43	343.90	457.48	406.50	372.72	321.75
ODP kg CFC-11 eq.	1.65E-05	1.75E-05	1.69E-05	1.65E-05	1.60E-05	1.65E-05	1.61E-05	1.58E-05	1.54E-05
EP kg N eq.	0.35	0.40	0.37	0.35	0.33	0.37	0.35	0.33	0.31
AP kg SO ₂ eq.	1.67	1.71	1.69	1.67	1.65	1.61	1.60	1.59	1.58
POCP kg O ₃ eq.	36.02	37.28	36.52	36.02	35.27	35.00	34.58	34.31	33.90
Use of primary resources									
RPR _E MJ, NCV	210.26	254.14	227.75	210.26	183.86	251.50	225.50	208.28	182.28
RPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRPR _E MJ, NCV	2598.87	2861.73	2703.63	2598.87	2440.78	2151.41	2100.12	2066.14	2014.85
NRPR _M MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Use of secondary resources									
SM kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
RSF MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
NRSF MJ, NCV	172.07	229.42	194.93	172.07	137.57	207.56	176.35	155.67	124.46
RE MJ, NCV	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Abiotic depletion potential									
ADPF MJ, LHV	966.32	1061.33	1004.19	966.32	909.18	1024.61	972.99	938.78	887.16
ADPe kg Sb	2.53E-04	2.64E-04	2.57E-04	2.53E-04	2.45E-04	2.63E-04	2.56E-04	2.51E-04	2.44E-04
Consumption of freshwater resources									
FW m ³	2.72	3.04	2.85	2.72	2.53	2.92	2.75	2.63	2.46
Waste and output flows									
HWD kg	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
NHWD kg	95.31	127.05	107.96	95.31	76.21	114.72	97.48	86.06	68.82
HLRW m ³	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09	1.83E-09
ILLRW m ³	5.59E-08	5.59E-08	5.59E-08	5.59E-08	5.59E-08	5.59E-08	5.59E-08	5.59E-08	5.59E-08
CRU kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MR kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EE kg	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Additional inventory parameters for transparency									
CCE kg CO ₂ eq.	198.44	264.58	224.80	198.44	158.65	239.87	203.80	179.90	143.84

References

American Concrete Institute (ACI) 211: Standard Practice for Selecting Proportions for Normal, Heavyweight, and Mass Concrete

American Concrete Institute (ACI) 318: Building Code Requirements for Structural Concrete ASTM International (ASTM) C94: Standard Specification for Ready-Mixed Concrete

Athena Sustainable Materials Institute A Cradle-to-Gate Life Cycle Assessment of Ready-Mixed Concrete Manufactured by CRMCA Members – Version 2.0; Prepared by the Athena Sustainable Materials Institute: May 2022.

Canadian Standards Association (CSA): A3000 Cementitious materials compendium

Canadian Standards Association (CSA) A23.1/A23.2: Concrete materials and methods of concrete construction/Test methods and standard practices for concrete

Construction Specifications Institute (CSI) MasterFormat Division 03-30-00 Cast-in-Place Concrete

EN 15804:2012 Sustainability of construction works – Environmental product declarations – Core rules for the product category of construction products.

European Federation of Concrete Admixture Associations (2006). EFCA Environmental Declarations for Admixtures. <https://www.efca.info/efca-publications/environmental/>

ISO 21930: 2017 Building construction – Sustainability in building construction – Environmental declaration of building products.

ISO 14025: 2006 Environmental labeling and declarations - Type III environmental declarations - Principles and procedures.

ISO 14044: 2006 Environmental management - Life cycle assessment - Requirements and guidelines. ISO 14040: 2006 Environmental management - Life cycle assessment - Principles and framework.

National Renewable Energy Laboratory 2014. U.S. Life Cycle Inventory Database. <https://www.lcacommmons.gov/>

NSF International (2015) NSF Program Operator Rules

NSF International, Product Category Rule Environmental Product Declarations, PCR for Concrete, V2.1, August 2021. 2021.<https://www.nsf.org/standards-development/product-category-rules>